

PETG White, 1.75 mm, 1 kg 3DP-PETG1.75-01-W

VERSATILE & EASY TO USE

- Polyethylene terephthalate (PETG) is an amorphous thermoplastic of the polyester family
- Perfect combination of clarity and strength. The clarity of PETG approaches that of Acrylic and impact resistance is close to Polycarbonate
- Easy to print with a variety of 3D printers





Specifications

Material: PETG, 1.75 mm diameter Weight: 1 kg/spool (2.2 lbs) Density at 240°C: 1.27 g/cm3 Melt Flow Index at g/10min, 200°C/ 5kg: 20 Melt Point: 220 260 °C Heat-Deflection-Temperature at 0.455 MPa: 60 80 °C Yield Strength at 5mm/min: 50 MPa Impact Strength: 8.7 KJ/m2 Ensile Break: 120 % Diameter: 1.75 ± 0.05 mm

System requirements

A 3D printer with 1.75 mm extruder of temperature around 240 $^\circ \text{C},$ suitable for PETG filament

Certificates



Features

- Very high strength filament
- Impact Resistant PETG is less brittle than acrylic, and is a lower cost alternative to polycarbonate.
- Chemical Resistant offers superior chemical resistance when compared with many other transparent plastics.
- Environmental friendly as it is considered 100% recyclable
- Very low shrinkage makes printing large flat surfaces a breeze
- Easily printed on any acrylic, glass, Kapton and other printing platform

Packaging

Q'ty in crtn, pcs Crtn volume, CUM Crtn weight, kgs Individual package size LxWxH: Carton size LxWxH: Country of origin Barcode Customs code 8 0.034 11.1 210x210x90 mm 430x430x185 mm CN 8716309090773 3916909000

Copyright $\ensuremath{\mathbb{C}}$ 2009–2020, Gembird Software Ltd.

Wittevrouwen 56 | 1358CD Almere | The Netherlands | Phone: +31-36-5211588 | www.gembird.nl | postmaster@gembird.n